

Technical Data Sheet Hm 2471 (UP GM 203)

Hm 2471 (UP GM 203)

Hm 2471 acc. DIN 7735 / UP GM 203 acc. EN 60893 – glass-mat reinforced unsaturated polyester hard laminate ("hartmatte"), NEMA equivalent GPO-3

Typical Properties

- Glass-mat reinforced polyester hard laminate ("hartmatte")
- NEMA equivalent GPO-3
- High electrical insulation performance
- Good resistance to arc tracking and creepage (CTI 600)
- Thermoset laminate (dimensionally stable)
- Good machinability
- Self-extinguishing (UL 94 V-0)
- Colour white (natural)

Typical Industries

- Electrical engineering and switchgear construction (LV/MV)
- Power supply and transformer engineering
- Mechanical and plant engineering
- Jig, fixture and tool making
- Test and measurement technology
- General mechanical component manufacturing

	Test Method	Unit	Value
Mechanical Properties			
Compressive Strength 23°C	ISO 604	N/mm ²	200
Flexural Strength 23°C	ISO 178	N/mm ²	130
Modulus of Elasticity (Flexural)	ISO 178	N/mm ²	8000
Tensile Strength	ISO 527	N/mm ²	70
Shear Strength to Laminations	EN 60893	N/mm ²	20
Notched Impact Strength (10°C)	ISO 179	kJ/m ²	150
Electrical Properties			
Comparative Tracking Index CTI	IEC 112	–	600
Dielectric Constant	DIN 53483	–	4.5
Insulation Resistance after Water Immersion	IEC 167	Ω	5 · 10 ⁸
Electric Strength ⊥	IEC 243-1	kV / 3 mm	27
Electric Strength	IEC 243-1	kV / 25 mm	35
Thermal Properties			
Limiting Temperature	IEC 216	°C	130
General Properties			
Density	ISO 1183	g/cm ³	1.8

	Test Method	Unit	Value
Water Absorption	ISO 62	%	0.2
Flammability Rating	UL 94	–	V-0
Colour			white (natural)

Hm 2471 (UP GM 203) is a glass-mat reinforced hard laminate made of unsaturated polyester resin ("hartmatte") to DIN 7735 / EN 60893, NEMA equivalent GPO-3. The values stated are typical properties subject to normal manufacturing tolerances; they serve as an aid to material selection and do not constitute a legally binding guarantee of specific properties. Actual values may vary slightly depending on manufacturer and sheet thickness. Hm 2471 (UP GM 203) is not declared suitable for direct food contact.

Liedtke
Kunststofftechnik.de